



EPDM Black 60 ShA Peroxide Cured

E60PC

EPDM Black 60 ShA. Peroxide Cured for enhanced performance. Offers reliable sealing properties in a temperature range from -50°C to +150°C, making it suitable for various applications.

Colour: Black

Operating Temperature range: -50°C to +150°C

Physical Property	Test Method	Unit	Typical Values
Hardness	ASTM D2240	ShA	60
Tensile Strength	ASTM D412	MPa	12.7
Elongation	ASTM D412	%	251
Specific Gravity	ASTM D297	g/cm ³	1.13
Compression Set	ASTM D395B	%	17
Tear Resistance	ASTM D624	N/mm	43
Low Temperature	ASTM D2137	°C	-50

Approvals/Special Features:

Peroxide Cured