



EPDM Black 70 ShA Peroxide Cured

E70PC

EPDM Black 70 ShA Peroxide Cured. Offers reliable sealing properties in a temperature range from -50°C to +150°C, making it suitable for various applications.

Colour: Black

Operating Temperature range: -50°C to +150°C

Physical Property	Test Method	Unit	Typical Values
Hardness	ASTM D2240	ShA	70
Tensile Strength	ASTM D412	MPa	11.6
Elongation	ASTM D412	%	266
Specific Gravity	ASTM D297	g/cm ³	1.19
Compression Set	ASTM D395B	%	17
Tear Resistance	ASTM D624	N/mm	34
Low Temperature	ASTM D2137	°C	-55
TR10	ASTM D1329	°C	-42

Approvals/Special Features:

Peroxide Cured