



EPDM Black 80 ShA Peroxide Cured

E802PC

EPDM Black 80 ShA Peroxide Cured. Operates effectively in a temperature range from -40°C to +150°C, making it suitable for various applications.

Colour: Black

Operating Temperature range: -40°C to +150°C

Physical Property	Test Method	Unit	Typical Values
Hardness	ASTM D2240	ShA	80
Tensile Strength	ASTM D412	MPa	13.1
Elongation	ASTM D412	%	173
Specific Gravity	ASTM D297	g/cm ³	1.21
Compression Set	ASTM D395B	%	19
Tear Resistance	ASTM D624	N/mm	52
Low Temperature	ASTM D2137	°C	-55
TR10	ASTM D1329	°C	-42.7

Approvals/Special Features:

Peroxide Cured