



FFKM Black 75 ShA

P2702B8

With a temperature range of -25°C to +275°C, this FFKM material is suitable for high-temperature sealing applications.

Colour: Black

Operating Temperature range: -25°C to +275°C

Physical Property	Test Method	Unit	Typical Values
Hardness	ASTM D2240	ShA	75
Tensile Strength	ASTM D1414	MPa	18
Elongation	ASTM D1414	%	145
Specific Gravity	ASTM D297	g/cm ³	1.98
Compression Set	ASTM D 395	%	18.5

Approvals/Special Features: