



FKM Brown 75 ShA

VBR75

VBR75 is a brown FKM rubber with a Shore A hardness of 75. Provides dependable sealing properties in a temperature range from -15°C to +200°C, suitable for various sealing applications.

Colour: Brown

Operating Temperature range: -15°C to +200°C

Physical Property	Test Method	Unit	Typical Values
Hardness	ASTM D2240	ShA	75
Tensile Strength	ASTM D412	MPa	15.2
Elongation	ASTM D412	%	154
Specific Gravity	ASTM D297	g/cm ³	2.1
Compression Set	ASTM D395B	%	14
Low Temperature	ASTM D2137	°C	-15
TR10	ASTM D1329	°C	-15

Approvals/Special Features: